

(19)

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 035 172 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
13.09.2000 Bulletin 2000/37

(51) Int. Cl. 7: C09B 55/00, C09D 11/00

(21) Application number: 00104167.2

(22) Date of filing: 29.02.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 12.03.1999 JP 6672299

(71) Applicant:
FUJI PHOTO FILM CO., LTD.
Kanagawa-ken, 250-0123 (JP)

(72) Inventors:
• Yamakawa, Katsuyoshi,
Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
• Motoki, Masuji,
Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)



• Asanuma, Naoki,
Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
• Suzuki, Ryo,
c/o Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
• Sato, Tadahisa,
c/o Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
• Mikoshiba, Hisashi,
c/o Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)

(74) Representative:
Grünecker, Kinkeldey,
Stockmair & Schwanhäusser
Anwaltssozietät
Maximilianstrasse 58
80538 München (DE)

(54) Azomethine compound and oily magenta ink

(57) An azomethine compound is represented by the formula (I).

(I)



and R^1 , L^1 , L^2 , R^3 and R^4 have 20 to 50 carbon atoms in total.

Description

FIELD OF THE INVENTION

- 5 [0001] The present invention relates to an azomethine compound. In detail, the invention relates to an azomethine compound suitable for a jet printing ink of magenta color.


BACKGROUND OF THE INVENTION


- 10 [0002] In an ink-jet recording method, images or characters are printed on image-receiving material with ink ejected from very fine nozzles. The ink-jet recording method can be conducted by using a relatively inexpensive apparatus (i.e., an ink-jet printer), as compared with other printing methods. Further, in proportion to improvement of the method, images of high qualities have been given recently. Now, the ink-jet recording method is one of the most popular image-recording methods.
- 15 [0003] Ink for the ink-jet recording method (i.e., jet printing ink) must not choke the fine nozzles. Since aqueous inks (aqueous solutions of dyes) hardly choke the nozzles, they are widely used. However, the aqueous inks have poor water resistance. Various means (described in Japanese Patent Provisional Publication Nos. 4(1992)-28776, 4(1992)-189876, 4(1992)-261478, 4(1992)-359071 and 4(1992)-359072) have been proposed to improve the water resistance of the aqueous inks or water-soluble dyes. In addition, the water-soluble dyes have poor light resistance.
- 20 [0004] Oil-soluble dyes (described in Japanese Patent Provisional Publication Nos. 1(1989)-170672, 3(1991)-221137, 7(1995)-96163, 8(1996)-218015, 9(1997)-3376, 9(1997)-241565, 9(1997)-286939 and 10(1998)-279873) have been proposed in place of the water-soluble dyes. The oil-soluble dyes are usually incorporated in microcapsules or soaked in polymers when they are used for ink-jet printing. Although the oil-soluble dyes have satisfying water resistance, they are unsatisfactory in color reproduction and color stability.

SUMMARY OF THE INVENTION

- [0005] Water-soluble dyes for ink-jet recording have poor resistance against water and light, while oil-soluble dyes are unsatisfactory in color reproduction and color stability.
- 30 [0006] An object of the present invention is to provide an oil-soluble dye excellent in color reproduction and color stability.
- [0007] Another object of the invention is to provide an azomethine compound suitable for a jet printing ink of magenta color.
- [0008] A further object of the invention is to provide an oily magenta ink for ink-jet recording.
- 35 [0009] The applicants have found an azomethine compound having light-absorption characteristics suitable for a magenta dye. The compound is oil-soluble, and is advantageously used in a preparation of an oily magenta ink for ink-jet recording.
- [0010] The present invention provides an azomethine compound represented by the formula (I):

(I)





15 R^1 is an alkyl group having 1 to 16 carbon atoms; R^2 is a halogen atom, an alkyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an amido group having 2 to 20 carbon atoms, an alkoxy carbonylamino group having 2 to 20 carbon atoms, nitro or cyano; R^3 is an alkyl group having 1 to 30 carbon atoms, an aryl group having 6 to 30 carbon atoms, an aryloxyalkyl group having 7 to 30 carbon atoms or an alkoxy carbonylalkyl group having 3 to 30 carbon atoms; R^4 is an alkyl group having 1 to 16 carbon atoms; L^1 is an alkylene group having 1 to 30 carbon atoms or an arylene group having 6 to 30 carbon atoms; L^2 is $-\text{CO}-\text{NH}-$, $-\text{SO}_2-\text{NH}-$, $-\text{O}-$, $-\text{O}-\text{CO}-$ or $-\text{O}-\text{CO}-\text{NH}-$; X is

20 cyano, an alkoxy carbonyl group having 2 to 19 carbon atoms, an alkylsulfonyl group having 1 to 18 carbon atoms, an arylsulfonyl group having 6 to 26 carbon atoms, sulfamoyl, an alkylsulfamoyl group having 1 to 18 carbon atoms or an arylsulfamoyl group having 6 to 26 carbon atoms; Y is hydrogen, a halogen atom, hydroxyl, an alkoxy group having 1 to 20 carbon atoms, an aryloxy group having 6 to 20 carbon atoms or an acyloxy group having 2 to 20 carbon atoms; m is 1, 2, 3 or 4; n is an integer of 1 to 18; p is 0, 1, 2, 3 or 4; and R^1 , L^1 , L^2 , R^3 and R^4 have 20 to 50 carbon atoms in total.

25 **[0011]** The invention also provides an oily magenta ink in which an azomethine dye represented by the formula (I) is dissolved in an organic solvent.


[0012] The azomethine compound represented by the formula (I) has excellent characteristics suitable for a magenta dye. Accordingly, the azomethine compound can be advantageously used in a preparation of an oily magenta ink for ink-jet recording.

30 **[0013]** Further, the azomethine compound represented by the formula (I) is excellent in stability to light and heat. Accordingly, the azomethine compound can be used a magenta dye that is excellent in a light resistance and in a heat resistance.


DETAILED DESCRIPTION OF THE INVENTION

35 **[0014]** The azomethine compound represented by the formula (I) can be classified into the three embodiments represented by the formulas (Ia), (Ib) and (Ic), respectively. The embodiment of the formula (Ia) is particularly preferred.


(Ia)



(Ib)



(Ic)



[0015] In the formulas (Ia) to (Ic), R¹ is an alkyl group having 1 to 16 carbon atoms. The alkyl group preferably has 1 to 12 carbon atoms, more preferably has 1 to 8 carbon atoms, further preferably has 1 to 6 carbon atoms, and most preferably has 1 to 4 carbon atoms. The alkyl group can have a branched chain. Examples of the alkyl groups include methyl and t-butyl.

[0016] In the formulas (Ia) to (Ic), R² is a halogen atom, an alkyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an amido group having 2 to 20 carbon atoms, an alkoxy-carbonylamino group having 2 to 20 carbon atoms, nitro or cyano.

[0017] The alkyl group preferably has 1 to 12 carbon atoms, more preferably has 1 to 8 carbon atoms, further preferably has 1 to 4 carbon atoms, and most preferably has 1 or 2 carbon atoms. The alkyl group can have a branched chain. Examples of the alkyl groups include methyl and ethyl.

[0018] The alkoxy group preferably has 1 to 12 carbon atoms, more preferably has 1 to 8 carbon atoms, further preferably has 1 to 4 carbon atoms, and most preferably has 1 or 2 carbon atoms. The alkoxy group can have a branched chain. Examples of the alkoxy groups include methoxy.

[0019] The amido group preferably has 2 to 12 carbon atoms, more preferably has 2 to 8 carbon atoms, further preferably has 2 to 6 carbon atoms, and most preferably has 3 or 4 carbon atoms. Examples of the amido groups include acetamido.

[0020] The alkoxy-carbonylamino group preferably has 2 to 12 carbon atoms, more preferably has 2 to 8 carbon atoms, further preferably has 2 to 6 carbon atoms, and most preferably has 2 or 3 carbon atoms. Examples of the alkoxy-carbonylamino groups include methoxycarbonylamino.

[0021] In the formulas (Ia) to (Ic), R³ is an alkyl group having 1 to 30 carbon atoms, an aryl group having 6 to 30

carbon atoms, an aryloxyalkyl group having 7 to 30 carbon atoms or an alkoxycarbonylalkyl group having 3 to 30 carbon atoms.

[0022] The alkyl group preferably has 2 to 25, more preferably has 3 to 20 carbon atoms, and most preferably has 4 to 16 carbon atoms. The alkyl group can have a branched chain.

[0023] Examples of the aryl groups include phenyl and naphthyl. Phenyl is preferred. The aryl group can have a substituent group. Examples of the substituent groups include a halogen atom, an alkyl group having 1 to 24 carbon atoms and an alkoxy group having 1 to 24 carbon atoms. The aryl group has 6 to 30 carbon atoms, preferably 6 to 25 carbon atoms, more preferably 6 to 20 carbon atoms, and most preferably 6 to 16 carbon atoms. The number of the carbon atoms means the number of the total carbon atoms contained in the aryl group and the substituent group.

[0024] The alkyl moiety of the aryloxyalkyl group can have a branched chain. The aryl moiety of the aryloxyalkyl group is preferably phenyl. The aryloxyalkyl group can have a substituent group. Examples of the substituent groups include a halogen atom, an alkyl group having 1 to 23 carbon atoms and an alkoxy group having 1 to 23 carbon atoms. The aryloxyalkyl group has 7 to 30 carbon atoms, preferably has 7 to 25 carbon atoms, more preferably 7 to 20 carbon atoms, and further preferably 7 to 16 carbon atoms. The number of the carbon atoms means the number of the total carbon atoms contained in the aryloxyalkyl group and the substituent group.

[0025] The alkoxycarbonylalkyl group preferably has 3 to 25 carbon atoms, more preferably has 4 to 20 carbon atoms, and most preferably has 5 to 16 carbon atoms. Each of the two alkyl moieties of the alkoxycarbonylalkyl group can have a branched chain.

[0026] In the formula (Ic), R^4 is an alkyl group having 1 to 16 carbon atoms. The alkyl group preferably has 1 to 12 carbon atoms, more preferably has 1 to 8 carbon atoms, further preferably has 1 to 6 carbon atoms, and most preferably has 1 to 4 carbon atoms. The alkyl group can have a branched chain. Examples of the alkyl groups include methyl and ethyl.

[0027] In the formulas (Ia) to (Ic), L^1 is an alkylene group having 1 to 30 carbon atoms or an arylene group having 6 to 30 carbon atoms.

[0028] The alkylene group preferably has 1 to 25 carbon atoms, more preferably has 2 to 20 carbon atoms, and most preferably has 2 to 16 carbon atoms. The alkylene group can have a branched chain.

[0029] Examples of the arylene groups include phenylene and naphthylene. Phenylene is preferred. The arylene group can have a substituent group. Examples of the substituent groups include a halogen atom, an alkyl group having 1 to 24 carbon atoms and an alkoxy group having 1 to 24 carbon atoms. The arylene group has 6 to 30 carbon atoms, preferably 6 to 25 carbon atoms, more preferably 6 to 20 carbon atoms, and most preferably 6 to 16 carbon atoms. The number of the carbon atoms means the number of the total carbon atoms contained in the arylene group and the substituent group. In the formulas (Ia) to (Ic), L^2 is $-CO-NH-$, $-SO_2-NH-$, $-O-$, $-O-CO-$ or $-O-CO-NH-$, in each of which the left side is attached to R^3 , and the right side is attached to L^1 .

[0030] In the formulas (Ia) to (Ic), X is cyano, an alkoxycarbonyl group having 2 to 19 carbon atoms, an alkylsulfonyl group having 1 to 18 carbon atoms, an arylsulfonyl group having 6 to 26 carbon atoms, sulfamoyl, an alkylsulfamoyl group having 1 to 18 carbon atoms or an arylsulfamoyl group having 6 to 26 carbon atoms. Cyano and an alkoxycarbonyl group having 2 to 19 carbon atoms are preferred, and cyano is most preferred.

[0031] The alkoxycarbonyl group preferably has 2 to 8 carbon atoms. Examples of the alkoxycarbonyl groups include methoxycarbonyl and dodecyloxycarbonyl.

[0032] The alkylsulfonyl group preferably has 1 to 7 carbon atoms. Examples of the alkylsulfonyl groups include methanesulfonyl.

[0033] The aryl moiety of the arylsulfonyl group is preferably phenyl. The arylsulfonyl group can have a substituent group. Examples of the substituent groups include a halogen atom, an alkyl group having 1 to 20 carbon atoms and an alkoxy group having 1 to 20 carbon atoms. The arylsulfonyl group has 6 to 26 carbon atom, and preferably has 6 to 15 carbon atoms. The number of the carbon atoms means the number of the total carbon atoms contained in the arylsulfonyl group and the substituent group. Examples of the arylsulfonyl groups include benzenesulfonyl.

[0034] The alkylsulfamoyl group preferably has 1 to 9 carbon atoms. Examples of the alkylsulfamoyl groups include methylsulfamoyl.

[0035] The aryl moiety of the arylsulfamoyl group is preferably phenyl. The arylsulfamoyl group can have a substituent group. Examples of the substituent groups include a halogen atom, an alkyl group having 1 to 20 carbon atoms and an alkoxy group having 1 to 20 carbon atoms. The arylsulfamoyl group has 6 to 26 carbon atoms, and preferably has 6 to 15 carbon atoms. The number of the carbon atoms means the number of the total carbon atoms contained in the arylsulfamoyl group and the substituent group. Examples of the arylsulfamoyl groups include phenylsulfamoyl.

[0036] In the formulas (Ia) to (Ic), Y is hydrogen, a halogen atom, hydroxyl, an alkoxy group having 1 to 20 carbon atoms, an aryloxy group having 6 to 20 carbon atoms or an acyloxy group having 2 to 20 carbon atoms. Hydrogen atom is particularly preferred.

[0037] The alkoxy group preferably has 1 to 12 carbon atoms, more preferably has 1 to 8 carbon atoms, further preferably has 1 to 4 carbon atoms, and most preferably has 1 or 2 carbon atoms. The alkoxy group can have a branched

chain. Examples of the alkoxy groups include methoxy and ethoxy.

[0038] The aryl moiety of the aryloxy group is preferably phenyl. The aryloxy group can have a substituent group. Examples of the substituent groups include a halogen atom, an alkyl group having 1 to 14 carbon atoms and an alkoxy group having 1 to 14 carbon atoms. The aryloxy group has 6 to 20 carbon atoms, and preferably has 6 to 15 carbon atoms. The number of the carbon atoms means the number of the total carbon atoms contained in the aryloxy group and the substituent group. Examples of the aryloxy groups include phenoxy.

[0039] The acyloxy group preferably has 1 to 12 carbon atoms, more preferably has 1 to 8 carbon atoms, further preferably has 1 to 4 carbon atoms, and most preferably has 2 or 3 carbon atoms. Examples of the acyloxy groups include acetoxy.

[0040] In the formulas (Ia) to (Ic), m is an integer of 1 to 4, preferably is an integer of 1 to 3, and more preferably is 1 or 2. In the case that m is 2, 3 or 4, $(CH_2)_m$ means an alkylene group of a straight chain.


[0041] In the formulas (Ia) to (Ic), n is an integer of 1 to 18, preferably is an integer of 1 to 14, more preferably is an integer of 1 or 10, further preferably is an integer of 1 to 8, and most preferably is an integer of 1 to 6. In the case that n is 2 or more, the alkylene group represented by C_nH_{2n} can have a branched chain.

[0042] In the formulas (Ia) to (Ic), p is 0, 1, 2, 3 or 4, preferably is 0, 1, 2 or 3, more preferably is 0, 1 or 2, further preferably is 0 or 1, and most preferably is 0. In the case that p is 2, 3 or 4, the groups represented by R^2 can be different from each other.

[0043] In the formulas (Ia) and (Ib), R^1 , L^1 , L^2 and R^3 have 20 to 50 carbon atoms in total. In the formula (Ic), R^2 , L^1 , L^2 , R^3 and R^4 have 20 to 50 carbon atoms in total. The total number of the carbon atoms preferably is 25 to 45.

[0044] The azomethine compound of the formula (I) preferably has a molecular weight of 600 to 2,000, and more preferably has a molecular weight of 800 to 1,500.

[0045] Examples of the azomethine compounds represented by the formula (I) are shown below.



(Ia-1)

[0046]

R^1 : CH_3 , R^{21} : H, R^{22} : H,
 R^3 : 1-(2,4-di-*t*-pentylphenoxy)heptyl,
 L^1 : $-CH_2-CH(CH_3)-$, L^2 : $-CO-NH-$, X: cyano,
Y: H, m: 2, n: 2,

[0047] Total number of carbon atoms in R^1 , L^1 , L^2 and R^3 : 28

(Ia-2)

[0048]

R^1 : CH_3 , R^{21} : H, R^{22} : H,
 R^3 : 2-octyloxy-5-*t*-octylphenyl,
 L^1 : $-CH_2-CH(CH_3)-$, L^2 : $-SO_2-NH-$, X: cyano,
Y: H, m: 2, n: 4,

[0049] Total number of carbon atoms in R¹, L¹, L² and R³: 26

(la-3)

[0050]

R¹: CH₃, R²¹: H, R²²: H,
R³: 2-octyloxy-5-(2-octyloxy-5-t-octylphenylsulfoneamido)phenyl,
L¹: -CH₂-CH(CH₃)-, L²: -SO₂-NH-, X: cyano,
Y: H, m: 2, n: 1,

[0051] Total number of carbon atoms in R¹, L¹, L² and R³: 40

(la-4)

[0052]

R¹: CH₃, R²¹: H, R²²: H,
R³: 2-tetradecyloxycarbonylethyl,
L¹: -CH₂-CH(CH₃)-, L²: -CO-NH-,
X: ethoxycarbonyl, Y: H, m: 2, n: 4,

[0053] Total number of carbon atoms in R¹, L¹, L² and R³: 22

(la-5)

[0054]

R¹: CH₃, R²¹: CH₃, R²²: H, R³: pentadecyl,
L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
Y: H, m: 2, n: 4,

[0055] Total number of carbon atoms in R¹, L¹, L² and R³: 23

(la-6)

[0056]

R¹: CH₃, R²¹: CH₃, R²²: H,
R³: 1-(2,4-di-t-pentylphenoxy)heptyl,
L¹: -CH₂-CH(CH₃)-, L²: -CO-NH-, X: cyano,
Y: OH, m: 2, n: 2,

[0057] Total number of carbon atoms in R¹, L¹, L² and R³: 28

(la-7)

[0058]

R¹: CH₃, R²¹: H, R²²: H, R³: octadecyl,
L¹: -CH₂-CH₂-, L²: -O-, X: methoxycarbonyl,
Y: H, m: 1, n: 2,

[0059] Total number of carbon atoms in R¹, L¹, L² and R³: 21

(la-8)

[0060]

5 R¹: CH₃, R²¹: H, R²²: H, R³: hexadecyl,
 L¹: -1,3-phenylene-, L²: -O-CO-, X: cyano,
 Y: H, m: 3, n: 4,

[0061] Total number of carbon atoms in R¹, L¹, L² and R³: 24

(la-9)

[0062]

15 R¹: t-C₄H₉, R²¹: H, R²²: H,
 R³: 1-(2,4-di-t-pentylphenoxy)pentyl,
 L¹: -CH₂-CH(CH₃)-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 2,

20 [0063] Total number of carbon atoms in R¹, L¹, L² and R³: 29

(la-10)

[0064]

25 R¹: t-C₄H₉, R²¹: H, R²²: H,
 R³: 2-(2-methoxyethoxy-5-t-octylphenyl),
 L¹: -CH₂-CH(CH₃)-, L²: -SO₂-NH-, X: cyano,
 Y: H, m: 2, n: 4,

30 [0065] Total number of carbon atoms in R¹, L¹, L² and R³: 24

(la-11)

[0066]

35 R¹: t-C₄H₉, R²¹: H, R²²: H, R³: tridecyl,
 L¹: -1,3-phenylene-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 2,

40 [0067] Total number of carbon atoms in R¹, L¹, L² and R³: 24

(la-12)

[0068]

45 R¹: t-C₄H₉, R²¹: H, R²²: H,
 R³: 2-tetradecyloxycarbonylethyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
 50 Y: H, m: 2, n: 4,

[0069] Total number of carbon atoms in R¹, L¹, L² and R³: 28

(la-13)

[0070]

55 R¹: t-C₄H₉, R²¹: H, R²²: H,

R³: 1-(2,4-di-t-pentylphenoxy)heptyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 2,

5 [0071] Total number of carbon atoms in R¹, L¹, L² and R³: 34

(la-14)

[0072]

10

R¹: t-C₄H₉, R²¹: H, R²²: H,
 R³: 1-(2,4-di-t-pentylphenoxy)heptyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 4,

15

[0073] Total number of carbon atoms in R¹, L¹, L² and R³: 34

(la-15)

20 [0074]

R¹: t-C₄H₉, R²¹: CH₃, R²²: H,
 R³: 1-(2,4-di-t-pentylphenoxy)heptyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
 25 Y: OH, m: 2, n: 2,

[0075] Total number of carbon atoms in R¹, L¹, L² and R³: 34

(la-16)

30

[0076]

R¹: t-C₄H₉, R²¹: CH₃, R²²: H,
 R³: 2-tetradecyloxycarbonylethyl,
 35 L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 4,

[0077] Total number of carbon atoms in R¹, L¹, L² and R³: 28

40 (la-17)

[0078]

R¹: t-C₄H₉, R²¹: CH₃, R²²: H, R³: heptadecyl,
 45 L¹: -1,2-phenylene-, L²: -CO-NH-,
 X: methoxycarbonyl, Y: H, m: 1, n: 1,

[0079] Total number of carbon atoms in R¹, L¹, L² and R³: 28

50 (la-18)

[0080]

R¹: t-C₄H₉, R²¹: NHCOCH₃, R²²: H,
 55 R³: hexadecyl, L¹: -1,3-phenylene-,
 L²: -SO₂-NH-, X: cyano, Y: acetoxy,
 m: 1, n: 2,

[0081] Total number of carbon atoms in R¹, L¹, L² and R³: 26

(la-19)

5 [0082]

R¹: t-C₄H₉, R²¹: OCH₃, R²²: H,
 R³: octadecyl, L¹: -1,4-phenylene-,
 L²: -O-, X: sulfamoyl, Y: phenoxy,
 10 m: 3, n: 2,

[0083] Total number of carbon atoms in R¹, L¹, L² and R³: 28

(la-20)

15

[0084]

R¹: t-C₄H₉, R²¹: H, R²²: OCH₃,
 R³: hexadecyl, L¹: -3-chloro-1,4-phenylene-,
 20 L²: -O-, X: methanesulfonyl, Y: methoxy,
 m: 4, n: 2,

[0085] Total number of carbon atoms in R¹, L¹, L² and R³: 26

25 (la-21)

[0086]

R¹: C₂H₅, R²¹: H, R²²: H, R³: pentadecyl,
 30 L¹: -CH₂-CH(CH₃)-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 2,

[0087] Total number of carbon atoms in R¹, L¹, L² and R³: 21

35 (la-22)

[0088]

R¹: C₃H₇, R²¹: H, R²²: H, R³: pentadecyl,
 40 L¹: -CH₂-CH(CH₃)-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 4,

[0089] Total number of carbon atoms in R¹, L¹, L² and R³: 22

45 (la-23)

[0090]

R¹: C₇H₁₅, R²¹: CH₃, R²²: H,
 50 R³: 2-tetradecyloxy-carbonyl-ethyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 4,

[0091] Total number of carbon atoms in R¹, L¹, L² and R³: 31

55

(Ia-24)

[0092]

5 R¹: C₄H₉, R²¹: H, R²²: H,
 R³: 2-tetradecyloxy carbonyl ethyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-,
 X: butoxycarbonyl, Y: H, m: 2, n: 2,

10 [0093] Total number of carbon atoms in R¹, L¹, L² and R³: 28

(Ia-25)

[0094]

15 R¹: C₃H₇, R²¹: H, R²²: H,
 R³: 2-tetradecyloxy carbonyl ethyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-, X: cyano,
 Y: OH, m: 3, n: 2,

20 [0095] Total number of carbon atoms in R¹, L¹, L² and R³: 27


(Ia-26)

[0096]

25 R¹: C₂H₅, R²¹: H, R²²: H,
 R³: 2-tetradecyloxy carbonyl ethyl,
 L¹: -1,4-phenylene-, L²: -CO-NH-,
 30 X: cyano, Y: methoxy, m: 3, n: 2,

[0097] Total number of carbon atoms in R¹, L¹, L² and R³: 26

(Ib-1) - (Ib-4)



(Ib-1)

[0098]

50 R¹: CH₃, R²: H,
 R³: 1-(2,4-di-*t*-butylphenoxy)heptyl,
 L¹: -1,3-phenylene-, L²: -CO-NH-,
 X: methanesulfonyl, Y: H, m: 2, n: 4,

55 [0099] Total number of carbon atoms in R¹, L¹, L² and R³: 29

(lb-2)

[0100]

- 5 R¹: CH₃, R²: CH₃, R³: tetradecyl,
 L¹: -3-chloro-1,4-phenylene-, L²: -O-,
 X: cyano, Y: OH, m: 2, n: 2,

[0101] Total number of carbon atoms in R¹, L¹, L² and R³: 21

(lb-3)

[0102]

- 15 R¹: CH₃, R²: NHCO₂CH₃, R³: hexadecyl,
 L¹: -1,2-phenylene-, L²: -O-,
 X: sulfamoyl, Y: H, m: 2, n: 1,

[0103] Total number of carbon atoms in R¹, L¹, L² and R³: 23


(lb-4)

[0104]

- 25 R¹: CH₃, R²: CN, R³: pentadecyl,
 L¹: -CH₂-CH(CH₃)-, L²: -CO-NH-,
 X: N,N-dimethylsulfamoyl, Y: H,
 m: 4, n: 1,

30 [0105] Total number of carbon atoms in R¹, L¹, L² and R³: 20

(Ic-1) - (Ic-2)



(Ic-1)

[0106]

- 50 R¹: CH₃, R³: heptadecyl, R⁴: CH₃,
 L¹: -CH₂-CH(CH₃)-, L²: -CO-NH-, X: cyano,
 Y: H, m: 2, n: 4,

55 [0107] Total number of carbon atoms in R¹, L¹, L², R³ and R⁴: 23

(Ic-2)


[0108]

5 R^1 : $t\text{-C}_4\text{H}_9$, R^3 : 2-tetradecyloxyethyl,
 R^4 : C_2H_5 , L^1 : -1,4-phenylene-,
 L^2 : -O-CO-NH-, X: cyano, Y: H,
 m: 2, n: 4,


10 [0109] Total number of carbon atoms in R^1 , L^1 , L^2 , R^3 and R^4 : 30

[0110] The azomethine compound of the formula (I) can be synthesized by referring to the method described in Japanese Patent Provisional Publication No. 4(1992)-126772. The azomethine compound can be synthesized by a reaction of an azole compound represented by the formula (II) with a p-phenylenediamine compound represented by the formula (III) under an oxidizing condition.

(II)



(III)



15 [0111] In the formulas (II) and (III), Z^1 , Z^2 , R^1 , R^2 , X, Y, m, n and p are the same as those described above for the formula (I); and R is a group eliminable in the reaction. Examples of the eliminable groups (R) include hydrogen, a halogen atom, a heterocyclic group and an aryloxy group.

20 [0112] Though a dye of the azomethine compound of the formula (I) has excellent light resistance, an anti-fading agent can further improve its light resistance. The anti-fading agent is described in "Shikizai (written in Japanese)", 797 70(1997). Particularly preferred examples of the anti-fading agents are spirochroman and spiroindane.

25 [0113] The azomethine compound of the formula (I) is preferably used as a magenta dye, particularly an oily magenta ink suitably used for ink-jet recording.

30 [0114] The oily magenta ink for ink-jet recording can be easily prepared according to known publications (for example, Japanese Patent Provisional Publication Nos. 3(1991)-231975, 11(1999)-158422, 11(1999)-172183).

[0115] Organic solvents employable for preparing the oily magenta ink are hydrocarbons, alcohols, ketones, ethers, esters, nitriles, amides, sulfoxides and sulfones. Esters and ketones are particularly preferred.

40 [0116] Examples of the hydrocarbons include petroleum ether, petroleum benzene, tetralin, decalin, 1-amylnaphthalene and methylnaphthalene.

45 [0117] Examples of the alcohols include ethanol, pentanol, heptanol, octanol, cyclohexanol, benzyl alcohol, phenylethyl alcohol, phenylpropyl alcohol, anise alcohol, ethylene glycol monoethyl ether, ethylene glycol monophenyl ether, diethylene glycol monoethyl ether, diethylene glycol monobutyl ether, propylene glycol monoethyl ether, propylene glycol monophenyl ether, dipropylene glycol monomethyl ether, dipropylene glycol monoethyl ether and tripropylene glycol monoethyl ether.

[0118] Examples of the ketones include methyl ethyl ketone, benzyl methyl ketone, diacetone alcohol and cyclohexanone.

[0119] Examples of the ethers include butyl phenyl ether, benzyl ethyl ether and hexyl ether.

50 [0120] Examples of the esters include ethyl acetate, amyl acetate, benzyl acetate, phenylethyl acetate, phenoxyethyl acetate, ethyl phenylacetate, benzyl propionate, ethyl benzoate, butyl benzoate, ethyl laurate, butyl laurate, isopropyl myristate, isopropyl palmitate, triethyl phosphate, tributyl phosphate, diethyl phthalate, diethyl malonate, dipropyl malonate, diethyl diethylmalonate, diethyl succinate, dibutyl succinate, diethyl glutarate, diethyl adipate, dibutyl adipate, di(2-methoxyethyl) adipate, diethyl sebacate, diethyl maleate, dibutyl maleate, dioctyl maleate, diethyl fumarate, dioctyl fumarate, 3-hexenyl cinnamate, ethylene glycol diacetate, ethylene glycol monoethyl ether acetate and propylene glycol diacetate.

55 [0121] Examples of the nitriles include acetonitrile.

[0122] Examples of the amides include formamide, N,N-dimethylformamide, N,N-dimethylacetamide, N-methyl-2-

pyrrolidone, N-vinyl-2-pyrrolidone and N,N-diethyldodecanamide.

[0123] Examples of the sulfoxides include dimethyl sulfoxide.

[0124] Examples of the sulfones include sulfolane.

[0125] Two or more organic solvents can be used in combination.

5 [0126] The oily magenta ink contains the azomethine compound preferably in an amount of 0.2 to 20 wt.%, and more preferably in an amount of 0.5 to 10 wt.%.

[0127] In addition to the azomethine compound and the organic solvent, the ink can contain additives such as viscosity controlling agent, surface tension controlling agent, specific resistance controlling agent, film-formation controlling agent, UV absorber, antioxidizing agent, anti-fading agent, anti-fungal agent, rust inhibitor, dispersing agent and surface active agent.

10 [0128] In ink-jet recording, droplets of the aforementioned oily magenta ink (jet printing ink) are ejected to record an image on recording paper (image-receiving material). In this case, the ink preferably has a viscosity of not more than 40 cp and a surface tension of 20 to 100 dyn/cm.

[0129] For forming a full-color image, oily inks of cyan and yellow hues can be used together with the oily magenta ink. Further, an oily ink of black hue can be used to control the tone of the image.


15 [0130] As the recording paper (image-receiving material) for ink-jet printing, coat paper is preferred from the viewpoints of quality and durability of the image. Recording paper containing polymer mordant is also preferred. The recording paper may contain an inorganic pigment. The recording paper preferably comprises a hydrophilic ink-receiving layer containing a hydrophilic binder. The binder is preferably hardened with a curing agent. Further, the recording paper may contain a matting agent. The layers constituting the recording paper may contain a surface active agent or an organic fluorine compound, and further may contain a polymer latex, anti-fading agent and a fluorescent whitening dye.

20 [0131] Ink-jet recording is usually conducted in an on-demand system or in a continuous system. As the head for ink-jet recording (i.e., jet head), some types such as bubble jet type, thermal jet type and ultrasonic type are known.

25 [0132] There are also some types of the ink-jet recording method. For example, in one type, many small droplets of thin ink (which is often referred to as "photo-ink") are jetted out. In another type, two or more inks having the same hue but different concentrations are used to improve image quality. Further, colorless and transparent ink can be also usable.

EXAMPLE 1

30 [0133]



[Synthesis of azomethine compound (Ia-12)]


55 [0134] In 1,000 ml of ethyl acetate, 87.9 g of 2-[4-[3-(tetradecyloxycarbonyl)propanoylamino]phenyl]-6-tert-butyl-7-chloropyrazolo[1,5-b][1,2,4]-triazole was dissolved. Independently, 400 ml of methanol and 100 g of sodium carbonate were dissolved in 750 ml of water. The prepared two solutions were mixed, and 39.1 g of 4-amino-N-butyl-N-(2-cyanoethyl)aniline was further added. The obtained solution was dropwise added for 1.5 hour to a solution in which 50.0 g of ammonium persulfate was dissolved in 300 ml of water. The resulting solution was made to react for 1 hour. After 1,000

ml of ethyl acetate and 1,000 ml of water were added, the organic phase was collected. The collected liquid was twice washed with 1,500 ml of water, and the solvent was distilled off. To the obtained oil, 300 ml of acetonitrile was added to precipitate a crystalline product. The product was collected and air-dried, and then recrystallized from 300 ml of methanol. Thus, 45 g of the azomethine compound (Ia-12) was prepared. The yield was 40%, and the melting point was 118-119°C.

[0135] The starting material in the procedure, namely 2[4-{3-(tetradecyloxycarbonyl)propanoylamino}phenyl]-6-tert-butyl-7-chloropyrazolo[1,5-b][1,2,4]-triazole, was beforehand synthesized according to the method described in Japanese Patent Publication No. 7(1995)-14941. Further, 4-amino-N-butyl-N-(2-cyanoethyl)-aniline was also beforehand prepared from N-(2-cyanoethyl)-aniline in the known manner (butylation, nitrosoation and reduction reactions).

EXAMPLE 2

[0136]



[Synthesis of azomethine compound (Ia-4)]


[0137] N-butylaniline and ethylacrylate were made to react to prepare N-butyl-N-(2-ethoxycarbonylethyl)aniline, which was then nitrosoated and reduced to synthesize 4-amino-N-butyl-N-(2-ethoxycarbonylethyl)aniline.

[0138] From the prepared compound, the azomethine compound (Ia-4) was synthesized in the same manner as described in Example 1.


EXAMPLE 3

[0139]


(Ia-1)




(Ia-6)




(Ia-13)



(Ia-14)



(Ia-15)



[Synthesis of azomethine compounds]

[0140] The azomethine compounds (Ia-1), (Ia-6), (Ia-13), (Ia-14) and (Ia-15) were synthesized in a similar manner to Example 1 or 2.

[0141] The melting points of the compounds (Ia-1) and (Ia-6) are lower than room temperature (i.e., they are in the form of oily liquid at room temperature). The melting point of the compound (Ia-13) was 132-133°C, the melting point of the compound (Ia-14) was 119-120°C, and the melting point of the compound (Ia-15) was 118-120°C.

EXAMPLE 4

[Preparation of oily magenta ink]

[0142] Each of the azomethine compounds (Ia-1), (Ia-6), (Ia-12), (Ia-13), (Ia-14) and (Ia-15) prepared in Examples 1 and 3 was dissolved in ethyl acetate, and thereby it was found that their solubilities are more than 10 wt.%. Thus, oily magenta inks were prepared.

[0143] Independently, each compound was also dissolved in methyl ethyl ketone, and thereby it was found that their solubilities are also more than 10 wt.%. Thus, other oily magenta inks were prepared.

EXAMPLE 5

[Measurement of absorption maximum and molar extinction coefficient]

- 5 [0144] With respect to each of the ethyl acetate-base magenta inks [ethyl acetate solutions of the compounds (Ia-1), (Ia-6), (Ia-12), (Ia-13), (Ia-14) and (Ia-15)] prepared in Example 4, the absorption maximum (λ_{\max}) and molar extinction coefficient (ϵ) were measured. The results are set forth in Table 1.

Table 1

Azomethine compound	Absorption maximum (λ_{\max})	Molar extinction coefficient (ϵ)
(Ia-1)	512 nm	5.0×10^4
(Ia-6)	522 nm	5.2×10^4
(Ia-12)	519 nm	4.8×10^4
(Ia-13)	517 nm	4.6×10^4
(Ia-14)	520 nm	4.8×10^4
(Ia-15)	532 nm	4.9×10^4

EXAMPLE 6

[Measurement of solubility]

- 25 [0145] With respect to each of the azomethine compounds (Ia-6), (Ia-12) and (Ia-14), 600 mg of the compound was placed in a lidded test tube. After 2 ml of ethyl acetate was added, the mixture was treated with an ultrasonic cleaner for 30 minutes. The resultant liquid was heated and stirred at 65°C for 1 hour, and then cooled to room temperature. After leaving the test tube in a constant temperature bath at 25°C for 20 hours, solid particles were filtered off with a micro filter having the pore size of 0.2 μm to prepare an oily magenta ink.


30 [0146] Each prepared ink was concentrated to measure the solubility, but solid (crystallite) was not deposited. This indicates that the solubility of each compound is more than 30 wt. %.

COMPARISON EXAMPLE 1


[Measurement of solubility]

- 40 [0147] With respect to each of the following azomethine compounds (X-1), (X-2), (X-3) and (X-4), 30 mg of the compound was placed in a lidded test tube. After 2 ml of ethyl acetate was added, the mixture was treated with an ultrasonic cleaner for 30 minutes. The resultant liquid was heated and stirred at 65°C for 1 hour, and then cooled to room temperature. After leaving the test tube in a constant temperature bath at 25°C for 20 hours, solid particles were filtered off with a micro filter having the pore size of 0.2 μm to prepare an oily magenta ink.


(X-1)




(X-2)



(X-3)



(X-4)



[0148] The azomethine compounds (X-1), (X-2), (X-3) and (X-4) correspond to the compounds 1, 6, 16 and 18 in Japanese Patent Provisional Publication No. 4(1992)-178646 (pages 11-13), respectively.

[0149] Each prepared ink was concentrated to measure the solubility. The results are set forth in Table 2.

COMPARISON EXAMPLE 2

[Measurement of absorption maximum]

[0150] With respect to each of the ethyl acetate-base magenta inks [ethyl acetate solutions of the compounds (X-1), (X-2), (X-3) and (X-4)] prepared in Comparison Example 1, the absorption maximum (λ_{\max}) was measured. The results are set forth in Table 2.



Table 2

Azomethine compound	Absorption maximum (λ_{\max})	Solubility
(Ia-6)	522 nm	30.2 wt.% or more
(Ia-12)	519 nm	30.1 wt.% or more
(Ia-14)	520 nm	30.1 wt.% or more
(X-1)	504 nm	0.18 wt. %
(X-2)	520 nm	0.29 wt. %
(X-3)	511 nm	1.72 wt. %
(X-4)	536 nm	0.63 wt. %

Claims

1. An azomethine compound represented by the formula (I):

(I)



R^1 is an alkyl group having 1 to 16 carbon atoms; R^2 is a halogen atom, an alkyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an amido group having 2 to 20 carbon atoms, an alkoxycarbonylamino group having 2 to 20 carbon atoms, nitro or cyano; R^3 is an alkyl group having 1 to 30 carbon atoms, an aryl group having 6 to 30 carbon atoms, an aryloxyalkyl group having 7 to 30 carbon atoms or an alkoxycarbonylalkyl group having 3 to 30 carbon atoms; R^4 is an alkyl group having 1 to 16 carbon atoms; L^1 is an alkylene group having 1 to 30 carbon atoms or an arylene group having 6 to 30 carbon atoms; L^2 is -CO-NH-, -SO₂-NH-, -O-, -O-CO- or -O-CO-NH-; X is cyano, an alkoxycarbonyl group having 2 to 19 carbon atoms, an alkylsulfonyl group having 1 to 18 carbon atoms, an arylsulfonyl group having 6 to 26 carbon atoms, sulfamoyl, an alkylsulfamoyl group having 1 to 18 carbon atoms or an arylsulfamoyl group having 6 to 26 carbon atoms; Y is hydrogen, a halogen atom, hydroxyl, an alkoxy group having 1 to 20 carbon atoms, an aryloxy group having 6 to 20 carbon atoms or an acyloxy group having 2 to 20 carbon atoms; m as 1, 2, 3 or 4; n as an integer of 1 to 18; p is 0, 1, 2, 3 or 4; and R^1 , L^1 , L^2 , R^3 and R^4 have 20 to 50 carbon atoms in total.

2. The azomethine compound as defined in claim 1, wherein R^1 is an alkyl group having 1 to 12 carbon atoms.
3. The azomethine compound as defined in claim 1, wherein R^2 is a halogen atom, an alkyl group having 1 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, an amido group having 2 to 12 carbon atoms, an alkoxycarbonylamino group having 2 to 12 carbon atoms, nitro or cyano.
4. The azomethine compound as defined in claim 1, wherein R^3 is an alkyl group having 1 to 25 carbon atoms, an aryl group having 6 to 25 carbon atoms, an aryloxyalkyl group having 7 to 25 carbon atoms or an alkoxycarbonylalkyl group having 3 to 25 carbon atoms.
5. The azomethine compound as defined in claim 1, wherein R^4 is an alkyl group having 1 to 12 carbon atoms.
6. The azomethine compound as defined in claim 1, wherein L^1 is an alkylene group having 1 to 25 carbon atoms or an arylene group having 6 to 25 carbon atoms.
7. The azomethine compound as defined in claim 1, wherein X is cyano or an alkoxycarbonyl group having 2 to 19 carbon atoms.
8. The azomethine compound as defined in claim 1, wherein Y is hydrogen.

9. The azomethine compound as defined in claim 1, wherein m is 1, 2 or 3.


10. The azomethine compound as defined in claim 1, wherein n is an integer of 1 to 14.

5 11. The azomethine compound as defined in claim 1, wherein p is 0, 1, 2 or 3.

12. The azomethine compound as defined in claim 1, wherein R¹, L¹, L², R³ and R⁴ have 25 to 45 carbon atoms in total.

10 13. An azomethine compound represented by the formula (Ia):



(Ia)




25 wherein R¹ is an alkyl group having 1 to 16 carbon atoms; R² is a halogen atom, an alkyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an amido group having 2 to 20 carbon atoms, an alkoxycarbonylamino group having 2 to 20 carbon atoms, nitro or cyano; R³ is an alkyl group having 1 to 30 carbon atoms, an aryl group having 6 to 30 carbon atoms, an aryloxyalkyl group having 7 to 30 carbon atoms or an alkoxycarbonylalkyl group having 3 to 30 carbon atoms; L¹ is an alkylene group having 1 to 30 carbon atoms or an arylene group having 6 to 30 carbon atoms; L² is -CO-NH-, -SO₂-NH-, -O-, -O-CO- or -O-CO-NH-; X is cyano, an alkoxy carbonyl group having 2 to 19 carbon atoms, an alkylsulfonyl group having 1 to 18 carbon atoms, an arylsulfonyl group having 6 to 26 carbon atoms, sulfamoyl, an alkylsulfamoyl group having 1 to 18 carbon atoms or an arylsulfamoyl group having 6 to 26 carbon atoms; Y is hydrogen, a halogen atom, hydroxyl, an alkoxy group having 1 to 20 carbon atoms, an aryloxy group having 6 to 20 carbon atoms or an acyloxy group having 2 to 20 carbon atoms; m is 1, 2, 3 or 4; n is an integer of 1 to 18; p is 0, 1, 2, 3 or 4; and R¹, L¹, L², R³ and R⁴ have 20 to 50 carbon atoms in total.

14. An oily magenta ink in which an azomethine dye represented by the formula (I) is dissolved in an organic solvent:

(I)



R^1 is an alkyl group having 1 to 16 carbon atoms; R^2 is a halogen atom, an alkyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an amido group having 2 to 20 carbon atoms, an alkoxycarbonylamino group having 2 to 20 carbon atoms, nitro or cyano; R^3 is an alkyl group having 1 to 30 carbon atoms, an aryl group having 6 to 30 carbon atoms, an aryloxyalkyl group having 7 to 30 carbon atoms or an alkoxycarbonylalkyl group having 3 to 30 carbon atoms; R^4 is an alkyl group having 1 to 16 carbon atoms; L^1 is an alkylene group having 1 to 30 carbon atoms or an arylene group having 6 to 30 carbon atoms; L^2 is $-CO-NH-$, $-SO_2-NH-$, $-O-$, $-O-CO-$ or $-O-CO-NH-$; X is cyano, an alkoxycarbonyl group having 2 to 19 carbon atoms, an alkylsulfonyl group having 1 to 18 carbon atoms, an arylsulfonyl group having 6 to 26 carbon atoms, sulfamoyl, an alkylsulfamoyl group having 1 to 18 carbon atoms or an arylsulfamoyl group having 6 to 26 carbon atoms; Y is hydrogen, a halogen atom, hydroxyl, an alkoxy group having 1 to 20 carbon atoms, an aryloxy group having 6 to 20 carbon atoms or an acyloxy group having 2 to 20 carbon atoms; m is 1, 2, 3 or 4; n is an integer of 1 to 18; p is 0, 1, 2, 3 or 4; and R^1 , L^1 , L^2 , R^3 and R^4 have 20 to 50 carbon atoms in total.



(19)

Eur päisches Patentamt
European Patent Office
Offic européen des brev ts



(11)

EP 1 035 172 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
27.11.2002 Bulletin 2002/48

(51) Int Cl.7: C09B 55/00, C09D 11/00

(43) Date of publication A2:
13.09.2000 Bulletin 2000/37

(21) Application number: 00104167.2

(22) Date of filing: 29.02.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 12.03.1999 JP 6672299

(71) Applicant: FUJI PHOTO FILM CO., LTD.
Kanagawa-ken, 250-0123 (JP)

(72) Inventors:
• Yamakawa, Katsuyoshi, Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)


- Motoki, Masuji, Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
- Asanuma, Naoki, Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
- Suzuki, Ryo, c/o Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
- Sato, Tadahisa, c/o Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)
- Mikoshiba, Hisashi, c/o Fuji Photo Film Co., Ltd.
Minami-ashigara-shi, Kanagawa, 250-0123 (JP)

(74) Representative: Grünecker, Kinkeldey,
Stockmair & Schwanhäusser Anwaltssozietät
Maximilianstrasse 58
80538 München (DE)


(54) Azomethine compound and oily magenta ink

(57) An azomethine compound is represented by the formula (I).

(I)




wherein



or

EP 1 035 172 A3



and R¹, L¹, L², R³ and R⁴ have 20 to 50 carbon atoms in total.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 10 4167

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X.D	DATABASE WPI Section Ch. Week 199147 Derwent Publications Ltd., London, GB; Class A82, AN 1991-344768 XP002215077 -& JP 03 231975 A (FUJI PHOTO FILM CO LTD) . 15 October 1991 (1991-10-15) * abstract *	1-14	C09B55/00 C09D11/00
D,Y	PATENT ABSTRACTS OF JAPAN vol. 016, no. 495 (P-1436), 14 October 1992 (1992-10-14) -& JP 04 178646 A (FUJI PHOTO FILM CO LTD), 25 June 1992 (1992-06-25) * abstract *	1-14	
Y	US 5 227 359 A (MIKOSHIBA HISASHI ET AL) 13 July 1993 (1993-07-13) * abstract; example 20 *	1-14	
Y	US 5 238 903 A (MIKOSHIBA HISASHI ET AL) 24 August 1993 (1993-08-24) * abstract; example 40 *	1-14	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C09B C09D
A	PATENT ABSTRACTS OF JAPAN vol. 018, no. 019 (C-1152), 13 January 1994 (1994-01-13) -& JP 05 255604 A (FUJI PHOTO FILM CO LTD), 5 October 1993 (1993-10-05) * abstract *	1-13	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 27 September 2002	Examiner Dauksch, H
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		I : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons & : member of the same patent family, corresponding document	

EPC FORM 1503 03 82 (Pst/Col)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 10 4167

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-09-2002

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
JP 3231975	A	15-10-1991	NONE		
JP 04178646	A	25-06-1992	JP	2964422 B2	18-10-1999
US 5227359	A	13-07-1993	JP	2747848 B2	06-05-1998
			JP	4090384 A	24-03-1992
US 5238903	A	24-08-1993	JP	2684436 B2	03-12-1997
			JP	3244593 A	31-10-1991
JP 05255604	A	05-10-1993	JP	2665642 B2	22-10-1997

EPO FORM P/419

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82